RTV silikone i blisterpakning
RTV silicone in blister pack

SKU: 300018

Dansk:

SANXI SORT RTV Silikone – Pakningsmasse

Laver næsten enhver pakning – øjeblikkeligt

Erstatter de fleste udskårne pakninger. Former sig til enhver form med det samme og hærder hurtigt. Modstår revner, krympning og forskydning forårsaget af termiske svingninger. Tætner også knastakselkæde-dæksler og differentiale-kapsler. Tørrer hårdt, men forbliver fleksibel. Tåler op til 260 °C. Modstår olie, vand, frostvæske og gearolie.

Brugsanvisning:

1. Rengør alle overflader grundigt. Fjern gamle pakningsrester og affedt overfladerne. Tør og fjern al olie og fedt.
2. Fjern hætten, punkter indersikringen, skru dysen på og skær den til den ønskede størrelse.
3. Påfør en jævn stribe (1,5–3 mm) rundt langs kanten af én af overfladerne. Sørg for at dække alle bolt- og skruehuller.
4. Vent 10 minutter, så silikonen får "skind". Saml derefter delene.

ADVARSEL:

Uhærdet tætningsmasse kan give irritation.
Undgå kontakt med øjne og hud.
VED KONTAKT: Skyl øjnene med vand og kontakt læge. Fjern silikone fra huden med tør klud eller papir.
Produktet afgiver eddikesyre under hærdning (lugter som eddike) – brug kun i godt ventilerede områder.

OPBEVARES UTILGÆNGELIGT FOR BØRN.

BEMÆRK:

- Bevar pakningens tykkelse ved samling
- Undgå at overspænde boltene
- Fjern overskydende silikone med tør klud eller sprit
- Silikonen tørrer på ca. 1 time
- Fuld hærdning og vedhæftning efter 24 timer
- Sæt hætten på efter brug

NBE PRODUCTION A/S

Kjeldgaardsvej 2
9300 Sæby
www.nbe.dk
www.nbe-shop.dk

RTV silikone i blisterpakning
RTV silicone in blister pack

SKU: 300018

English:

SANXI BLACK RTV Silicone – Gasket Maker

Creates Almost Any Gasket – Instantly

Replaces most pre-cut gaskets. Instantly conforms to any shape and cures quickly. Resists cracking, shrinking, and shifting caused by thermal fluctuations. Also seals camshaft chain covers and differential housings. Dries hard but remains flexible. Withstands temperatures up to 260 °C. Resistant to oil, water, antifreeze, and gear oil.

Instructions for Use:

1. Clean all surfaces thoroughly. Remove any gasket residue and degrease surfaces. Wipe off all oil and grease.
2. Remove the cap, puncture the inner seal, screw on the nozzle, and cut to the desired size.
3. Apply an even bead (1.5–3 mm) along the edge of one surface. Make sure to cover all bolt and screw holes.
4. Wait 10 minutes for the silicone to "skin." Then assemble the parts.

WARNING:

Uncured sealant may cause irritation.
Avoid contact with eyes and skin.
IF CONTACT OCCURS: Rinse eyes with water and contact a doctor. Remove silicone from skin with a dry cloth or paper.
The product releases acetic acid while curing (smells like vinegar) – use only in well-ventilated areas.

KEEP OUT OF REACH OF CHILDREN.

NOTE:

- Maintain gasket thickness during assembly
- Avoid over-tightening bolts
- Remove excess silicone with a dry cloth or alcohol
- Silicone dries in approx. 1 hour
- Fully cured and bonded after 24 hours
- Replace cap after use